

超塑烯® UE630

EVATHENE® UE630

乙烯醋酸乙烯酯共聚合樹脂



ETHYLENE-VINYL ACETATE COPOLYMER RESINS

概述

超塑烯® UE630 是一種乙烯醋酸乙烯酯共聚合樹脂，可運用在注塑發泡與模壓發泡成型、平板擠壓、吹膜成型、鑄膜擠壓及共擠壓的設備。

Description

EVATHENE® UE630 is an ethylene-vinyl acetate copolymer resin (EVA) for use in foam injection, foam compression molding, sheet extrusion, blown molding, casting and co-extrusion machine.

特性

- ◇ 柔軟
- ◇ 彈性
- ◇ 抗外界應力龜裂性很強
- ◇ 低溫柔軟性很好

Characteristics

- ◇ Flexibility
- ◇ Elasticity
- ◇ Great resistance to environmental stress cracking
- ◇ Low temperature flexibility

應用

1. 鞋材發泡
2. 食品包裝

Applications

1. Shoe sole foaming
2. Food packaging

物理性質 Physical Properties

項目 Properties	試驗方法 Test Method	數 值 Typical Value
VA 含量 VA Content (wt%)	USI	16
熔融指數 Melt Index (g/10min)	ASTM D1238	1.5
密度 Density (g/cm ³)	ASTM D792	0.937
斷裂點抗張強度(模片) Tensile Strength(Molded) (Break) (kg/ cm ²)	ASTM D638	170
斷裂點伸長率 (模片) Ultimate Elongation(Molded) (%)	ASTM D638	700
低溫脆裂溫度 Low Temperature Brittleness(°C/F50)	ASTM D746	<-76
衛氏軟化溫度 Vicat Softening Temperature (°C)	ASTM D1525	67
熔點 Melt Point (°C)	ASTM D3418	89
硬度(蕭氏 A) Hardness (Shore A)	ASTM D2240	91

據本公司所知，上述資料應屬正確無誤，惟因使用時之情況非受本公司管制，所以本公司對上述所作之一切建議，恕不負責保證之責。
The information contained herein is, to our best knowledge, true and accurate. However, since conditions of use are beyond our control, all risks of such use are assumed by users.