

百塑烯® NA208 PAXOTHENE® NA208 低密度聚乙烯樹脂 LOW DENSITY POLYETHYLENE RESINS



概述

百塑烯® NA208 是一種低密度聚乙烯樹脂，可運用在粉末塗膠與射出成型。

Description

PAXOTHENE® NA208 is a low density polyethylene resin (LDPE) for use in power coating and injection molding.

特性

- ◇ 高流動性
- ◇ 卓越的光澤
- ◇ 韌性好
- ◇ 剛性好

Characteristics

- ◇ High flowability
- ◇ Outstanding gloss
- ◇ Good toughness
- ◇ Good stiffness

應用

1. 家庭用品
2. 奶粉罐軟蓋
3. 玩具
4. 聖誕燈泡
5. 塑膠樹的主幹

Applications

1. Housewares
2. PE plastic lid for milk powder can
3. Toys
4. Christmas mini lights
5. Plastic tree trunk

物理性質 Physical Properties

項目 Properties	試驗方法 Test Method	數 值 Typical Value
熔融指數 Melt Index (g/10min)	ASTM D1238	26
密度 Density (g/cm ³)	ASTM D1505	0.923
降伏點抗張強度(射出片) Yield Point Tensile Strength (Injected) (kg/cm ²)	ASTM D638	95
斷裂點抗張強度(射出片) Break Point Tensile Strength (Injected) (kg/cm ²)	ASTM D638	100
斷裂點伸長率(射出片) Ultimate Elongation(Injected) (%)	ASTM D638	120
抗低溫脆裂性 Low Temperature Brittleness(°C/F50)	ASTM D746	<-60
衛氏軟化溫度 Vicat Softening Point(°C)	ASTM D1525	93
熔點 Melt Point (°C)	ASTM D3418	112
硬度(蕭氏 D)Hardness (Shore D)	ASTM D2240	53

據本公司所知，上述資料應屬正確無誤，惟因使用時之情況非受本公司管制，所以本公司對上述所作之一切建議，恕不負保證之責。
The information contained herein is, to our best knowledge, true and accurate. However, since conditions of use are beyond our control, all risks of such use are assumed by users