

FREVA™ FA-701

Complex Flame Retardant

FREVA™ FA-701 is a high-performance, halogen-free flame retardant with excellent effectiveness for epoxy resins. This special product has a high melting point and superior heat resistance, and offers excellent compatibility with epoxy resins, thereby enhancing processing efficiency.

Features

- Composite formulation free from halogens, heavy metals, and REACH Substances of Very High Concern (SVHC)
- High melting point and excellent heat resistance
- Non-hygroscopic and insoluble in water, acetone, methyl ethyl ketone (MEK), toluene, and other common organic solvents
- It offers good hydrolysis resistance
- It can be dispersed in solvents like acetone or methyl ethyl ketone (MEK)

Technical Data:

| Item | Unit | Value |
|---------------------------|-------------------|--------------|
| Appearance | -- | White Powder |
| Particle Size | D50,um | 10 max. |
| Specific Gravity | g/cm ³ | 0.35-0.45 |
| Decomposition Temperature | °C | > 300 |
| Phosphorus Content | % | 16-18 |
| Solubility in water | g/100ml | 0.5 max. |

➤ The above data are based on laboratory measurements and are intended as general guidelines. They do not necessarily guarantee identical results in other settings.

Package

- Available in 20-kg/pack

Storage

- Store in a dry, sealed environment, avoiding exposure to moisture or humid conditions.

Shelf Life

- Minimum shelf life is 12 months from the date of shipping when stored according to the said conditions.

Safety :

- Additional safety data and handling instructions are available in our current Safety Data Sheet (SDS). When disposing of this product in accordance with regulations, it should be treated as special waste and sent to an appropriate incineration facility.

Values included in this data sheet are based on limited laboratory test specimens. These values are typical values and are not meant to be used for setting maximum or minimum values for specification purposes. Any determination of the suitability of the materials shown in this property data sheet for use by the end user is the sole responsibility of the user, who must assure themselves that the material as subsequently processed meets the need of his particular product or use. To the best of our knowledge the information in this publication is accurate and reliable, USI does not assume any liability whatsoever for the accuracy of this information.