



EVATHENE®

超塑烯®

ETHYLENE-VINYL ACETATE COPOLYMER RESINS

乙烯醋酸乙烯酯共聚树脂

产品 Products	单位 UNIT	检验方法 TEST METHOD (ASTM)	发泡 Foaming										油墨 Ink	
			UE629	UE630	UE632	UE659	UE33002	UE3302	UE3312	UE3330	UE4003	UE4055	UE40K	
物性 Physical Properties														
主要用途 MAIN APPLICATIONS			<ul style="list-style-type: none"> 鞋材发泡 食品包装 	<ul style="list-style-type: none"> 鞋材发泡 食品包装 	<ul style="list-style-type: none"> 鞋材发泡 替代软质 PVC、橡胶与其他弹性材料 	<ul style="list-style-type: none"> 鞋材发泡 配制热熔胶 电线电缆掺合树脂 	<ul style="list-style-type: none"> 鞋材发泡 电线电缆掺合树脂 	<ul style="list-style-type: none"> 鞋材发泡 一般掺合应用 	<ul style="list-style-type: none"> 鞋材发泡 电线电缆掺合树脂 	<ul style="list-style-type: none"> 鞋材发泡 一般掺合应用 	<ul style="list-style-type: none"> 鞋材发泡 一般掺合应用 	<ul style="list-style-type: none"> 鞋材发泡 热熔胶 	<ul style="list-style-type: none"> 配制油墨 热熔胶 	
VA 含量 VA CONTENT	重量百分率 wt %	USI	18	16	22	25	33	33	33	33	40	40	41	
熔值 MELT INDEX	克/10 分 g/10min	D1238	2.5	1.5	2.2	2.0	0.2	2	12	30	3	55	65	
密度 DENSITY	克/立方公分 g/cm³	D792	0.939	0.937	0.942	0.947	0.956	0.956	0.958	0.956	0.967	0.966	0.968	
断裂点抗张强度 BREAK POINT TENSILE STRENGTH 模片(MOLDED)	公斤/平方公分 kg/cm²	D638	180	170	170	210	110	100	90	70	80	40	38	
伸长率 ELONGATION 模片(MOLDED)	百分率 %	D638	750	700	820	890	710	1000	1000	900	>1000	>1000	>1000	
低温脆裂温度 LOW TEMPERATURE BRITTLENESS	度/半数破坏 °C /F50*	D746	<-76	<-76	<-76	<-76	-	-	<-76	-	-	-	-	
卫氏软化温度 VICAT SOFTENING TEMPERATURE	度 °C	D1525	64	67	58	54	-	-	-	-	-	-	-	
环球软化温度 RING & BALL SOFTENING TEMP.	度 °C	E28	-	-	-	-	-	-	-	113	-	105	103	
熔点 MELTING POINT	度 °C	D3418	86	89	82	77	64	64	64	64	48	48	45	
硬度 HARDNESS Shore A	萧氏 A Shore A	D2240	90	91	86	84	70	65	65	63	43	40	38	

据本公司所知，上述数据应属正确无误，惟因使用时之情况非受本公司管制，所以本公司对上述所作之一切建议，恕不负保证之责。使用上述或其它来源之数据，所发生之一切责任，概与本公司无涉，所有风险，应由使用者自行承担。再者，本数据所述事项，绝不能解释为诱导或建议使用与现在或未来的专利权有抵触之任何加工方法或产品。To our best knowledge, the information contained herein is true and accurate. However, since conditions of use are beyond our control, all recommendations or suggests are presented without guarantee or responsibility on our part. We disclaim all liability in connection with the use of information contained herein or otherwise. All risks of such use are assumed by the user. Furthermore, nothing contained herein shall be construed as an inducement or recommendation to be used in any process or any product in conflict with existing or future patents.

F50*: 50% failure F50*: 50%破裂或脆裂



EVATHENE®

超塑烯®

ETHYLENE-VINYL ACETATE COPOLYMER RESINS

乙烯醋酸乙烯酯共聚树脂

产品 Products	单位 UNIT	检验方法 TEST METHOD (ASTM)	注塑 / 热熔胶 Injection Molding / Hot Melt								涂胶 Coating	太阳能电池封装膜 Solar Cell Encapsulation	
			UE633	UE612-04	UE649-04	UE634-04	UE638-04	UE639-04	UE653-04	UE647-04	UE654-04	UE508	UE2828
物性 Physical Properties													
主要用途 MAIN APPLICATIONS			<ul style="list-style-type: none"> • 配制热熔胶 • 挤压涂覆 • Hot melt adhesives • Extrusion coating	<ul style="list-style-type: none"> • 配制热熔胶 • Hot melt adhesives	<ul style="list-style-type: none"> • 配制热熔胶 • Hot melt adhesives	<ul style="list-style-type: none"> • 配制热熔胶 • 鞋材发泡 • 电线电缆掺合树脂 • Hot melt adhesives • Shoe sole foaming • Wire & Cable Compounds	<ul style="list-style-type: none"> • 配制热熔胶 • Hot melt adhesives	<ul style="list-style-type: none"> • 配制热熔胶 • Hot melt adhesives	<ul style="list-style-type: none"> • 配制热熔胶 • Hot melt adhesives	<ul style="list-style-type: none"> • 配制热熔胶 • 电线电缆掺合树脂 • 一般掺合应用 • Hot melt adhesives • Wire & Cable Compounds • General Compounding	<ul style="list-style-type: none"> • 粉末压烫贴合 (用于不织布热熔胶) • Powder Hot Melt (for hot melt adhesion of non-woven-fabric)	<ul style="list-style-type: none"> • 太阳能电池封装膜 • Solar Cell Encapsulation	
VA 含量 VA CONTENT	重量百分率 wt %	USI	19	19	19	28	28	28	28	28	33	8	28
熔 值 MELT INDEX	克/10分 g/10min	D1238	20	150	400	6	18	150	400	800	30	85	25
密 度 DENSITY	克/立方公分 g/cm³	D792	0.938	0.937	0.934	0.948	0.948	0.945	0.942	0.940	0.956	0.925	0.948
断裂点抗张强度 BREAK POINT TENSILE STRENGTH 模片 (MOLDED)	公斤/平方公分 kg/cm²	D638	130	55	30	180	125	40	30	—	70	80	—
伸 长 率 ELONGATION 模片 (MOLDED)	百分率 %	D638	790	630	300	830	900	800	500	—	900	400	—
低温脆裂温度 LOW TEMPERATURE BRITTLENESS	度/半数破坏 °C /F50*	D746	<-76	<-40	<-30	<-76	<-76	<-30	<-30	—	—	<-76	—
卫氏软化温度 VICAT SOFTENING TEMPERATURE	度 °C	D1525	60	47	39	45	42	40	37	—	—	70	—
环球软化温度 RING & BALL SOFTENING TEMP.	度 °C	E28	—	98	91	145	125	89	80	80	113	-	—
熔 点 MELTING POINT	度 °C	D3418	83	82	78	73	72	67	65	63	64	96	72
硬 度 HARDNESS Shore A	肖氏 A Shore A	D2240	88	86	81	78	75	67	63	54	63	94	74

据本公司所知，上述数据应属正确无误，惟因使用时之情况非受本公司管制，所以本公司对上述所作之一切建议，恕不负保证之责。使用上述或其它来源之数据，所发生之一切责任，概与本公司无涉，所有风险，应由使用者自行承担。再者，本数据所述事项，绝不能解释为诱导或建议使用与现在或未来的专利权有抵触之任何加工方法或产品。To our best knowledge, the information contained herein is true and accurate. However, since conditions of use are beyond our control, all recommendations or suggests are presented without guarantee or responsibility on our part. We disclaim all liability in connection with the use of information contained herein or otherwise. All risks of such use are assumed by the user. Furthermore, nothing contained herein shall be construed as an inducement or recommendation to be used in any process or any product in conflict with existing or future patents.

F50*: 50% failure F50*: 50%破裂或脆裂



UNITHENE®

联塑烯®

HIGH DENSITY POLYETHYLENE RESINS

高密度聚乙烯树脂

产 品 Products	单位 UNIT	检 验 方 法 TEST METHOD (ASTM)	注 塑 成 型 Injection Molding									
			挤 压 Extrusion	LH901								
物 性 Physical Properties			LH901	LH503	LH506	LH606	LH606-13	LH514	LH523	LH5544	LH5564	LH5590
主要用途 MAIN APPLICATIONS			<ul style="list-style-type: none"> • 绳子 • 渔网、沙窗网与滤网 • 防水布、帆布与积层布 • 蚊帐 • 编织袋 • Rope • Fishing net, windows screen and filters • Tarpaulin, canvas and laminated cloth • Mosquito nets • Woven sack 	<ul style="list-style-type: none"> • 瓶盖 • 运动护膝及护肘 • 栈板 • Mineral water caps • Sports knee and elbow pads • Pallets 	<ul style="list-style-type: none"> • 运动用具 • 工业用箱 • Sport utensils • Industrial cases 	<ul style="list-style-type: none"> • 水果箱、家庭用具、栈板 • 食品容器 • 蚊帐 • Fruit crates, housewares, transportation crates • Food containers • Mosquito nets 	<ul style="list-style-type: none"> • 啤酒箱、水果箱 • 食品容器 • 栈板 • Beer crates, fruit crates • Food containers • Pallets 	<ul style="list-style-type: none"> • 家庭用品 • 玩具 • Housewares • Toys 	<ul style="list-style-type: none"> • 沙滩车外壳 • 硅胶管 • ATV plastic body • Silicone sealant tube 	<ul style="list-style-type: none"> • 熔融浸渍工法 • 粉末塗膠 • 薄壁容器 • 色母造粒 • Melt impregnation • Powder coating • Thin wall container • Master batch 	<ul style="list-style-type: none"> • 熔融浸渍工法 • 粉末塗膠 • 薄壁容器 • 色母造粒 • Melt impregnation • Powder coating • Thin wall container • Master batch 	<ul style="list-style-type: none"> • 粉末塗膠 • 薄壁容器 • 色母造粒 • Powder coating • Thin wall container • Master batch
熔 值 MELT INDEX	克/10分 g/10min	D1238	0.95	4.1	5.5	6.0	6.0	12	23	44	64	90
密 度 DENSITY	克/立方公分 g/cm³	D792	0.953	0.956	0.955	0.962	0.962	0.956	0.956	0.955	0.955	0.955
降伏点抗张强度 YIELD POINT TENSILE STRENGTH 模片(MOLDED)	公斤/平方公分 kg/cm²	D638	250	250	250	310	320	250	230	250	250	250
伸 长 率 ELONGATION 模片(MOLDED)	百分率 %	D638	1100	600	760	600	620	550	300	200	170	20
抗 冲 击 强 度 IZOD IMPACT STRENGTH	公斤公分/公分 kg-cm/cm	D256	55	12	9	7.0	7.0	4.0	3.5	3.2	2.9	2.7
弹性系数(模片) 1% SECANT MODULUS (MOLDED)	公斤/平方公分 kg/cm²	D638	7400	8500	8400	9900	10000	7800	7600	—	—	—
扭 转 刚 性 TORSIONAL STIFFNESS	公斤/平方公分 kg/cm²	D1043	6100	10500	10000	12500	12500	9600	9200	—	—	—
弯 曲 刚 性 FLEXURAL STIFFNESS	公斤/平方公分 kg/cm²	D747	11000	9500	9200	9900	9900	8300	8200	—	—	—
低温脆裂温度 LOW TEMPERATURE BRITTLNESS	度/半数破坏 °C /F50°	D746	<-76	<-76	<-76	<-76	<-76	<-76	<-76	—	—	—
卫氏软化温度 VICAT SOFTENING TEMPERATURE	度 °C	D1525	125	125	125	127	127	125	123	120	120	120
熔 点 MELTING POINT	度 °C	D3418	131	132	132	135	135	132	129	128	128	128
硬 度 HARDNESS	萧氏 D Shore D	D2240	68	68	68	69	69	68	68	68	68	68

F50*: 50% failure F50*: 50%破裂或脆裂

据本公司所知，上述数据应属正确无误，惟因使用时之情况非受本公司管制，所以本公司对上述所作之一切建议，恕不负保证之责。使用上述或其它来源之数据，所发生之一切责任，概与本公司无涉，所有风险，应由使用者自行承担。再者，本数据所述事项，绝不能解释为诱导或建议使用与现在或未来的专利权有抵触之任何加工方法或产品。To our best knowledge, the information contained herein is true and accurate. However, since conditions of use are beyond our control, all recommendations or suggests are presented without guarantee or responsibility on our part. We disclaim all liability in connection with the use of information contained herein or otherwise. All risks of such use are assumed by the user. Furthermore, nothing contained herein shall be construed as an inducement or recommendation to be used in any process or any product in conflict with existing or future patents.

公元二〇二一年八月发行
ISSUED IN August, 2021



PAXOTHENE® 百塑烯®

LOW DENSITY POLYETHYLENE RESINS
低密度聚乙烯树脂

LINATHENE® 线塑烯®

LINEAR LOW DENSITY POLYETHYLENE RESINS
线性低密度聚乙烯树脂

物性 Physical Properties	产品 Products	单位 UNIT	百塑烯® PAXOTHENE®				线塑烯® LINATHENE®				
			吹膜 Blown Film		注塑成型 Injection Molding		吹膜 / 铸膜 挤压 Blown Film / Casting Film				滚塑成型 Rotomolding
			NA112-27	NA207-66	NA208	NA248	LL110	LL115C	LL120	LL120C	LL405
主要用途 MAIN APPLICATIONS			<ul style="list-style-type: none"> 手提袋、冷藏袋与夹链袋 小型药水瓶 Shopping bag, frozen food bag and reclosable bag Eye drop bottle 	<ul style="list-style-type: none"> 包装袋 塑料树的树干 Bags Plastic tree trunk 	<ul style="list-style-type: none"> 家庭用品 奶粉罐软盖 玩具 圣诞灯泡 Housewares PE plastic lid for milk powder can Toys Christmas mini lights 	<ul style="list-style-type: none"> 塑料花或叶部 奶粉罐软盖 Artificial flowers or leaves PE plastic lid for milk powder can 	<ul style="list-style-type: none"> 重包装袋 内衬膜 冷冻袋 Heavy duty bags Suit Interlining Frozen food bags 	<ul style="list-style-type: none"> 伸缩包装膜 保鲜膜 农业用膜 Stretch film Plastic wrap Agricultural film 	<ul style="list-style-type: none"> 内衬膜 西装袋 冷冻袋 Sut Interlining Garment bag Frozen food bags 	<ul style="list-style-type: none"> 伸缩包装膜 保鲜膜 农业用膜 Stretch film Plastic wrap Agricultural film 	<ul style="list-style-type: none"> 化学品的储槽、水桶 流动厕所 交通护栏 溜滑梯 Storage tanks for chemicals or water Mobile toilet Portable traffic barrier Plastic slide
熔 值 MELT INDEX	克/10分 g/10min	D1238	3.0	8.0	22	48	1.0	1.2	2.0	2.0	5.3
密 度 DENSITY	克/立方公分 g/cm3	D792 D1505	- 0.919	- 0.919	- 0.918	- 0.916	0.920 -	0.919 -	0.922 -	0.919 -	0.936 -
降伏点抗张强度 YIELD POINT TENSILE STRENGTH A.模片(MOLDED) B.薄膜(FILM)MD*/TD**	公斤/平方公分 kg/cm2	A. D638 B. D882	B. 91/91	B. 98/100	A. 90	A. 80	B. 100/90	-	B. 115/100	B. 105/95	A. 190
断裂点抗张强度 BREAK POINT TENSILE STRENGTH A.模片(MOLDED) B.薄膜(FILM)MD*/TD**	公斤/平方公分 kg/cm2	A. D638 B. D882	B. 190/154	B. 190/135	A. 110	A. 80	B. 220/160	B. 300/200	B. 250/180	B. 240/170	-
伸 长 率 ELONGATION A.模片(MOLDED) B.薄膜(FILM)MD*/TD**	百分率 %	A. D638 B. D882	B. 340/550	B. 350/480	A. 120	A. 240	B. 500/600	B. 510/650	B. 450/550	B. 500/600	A. 900
低温脆裂温度 LOW TEMPERATURE BRITTLINESS	度/半数破坏 °C /F50*	D746	<-76	<-76	-60	-37	<-76	<-76	<-76	<-76	<-76
卫氏软化温度 VICAT SOFTENING TEMPERATURE	度 °C	D1525	100	100	96	80	102	102	103	102	115
熔 点 MELTING POINT	度 °C	D3418	108	109	108	100	122	122	122	122	125
硬 度 HARDNESS	肖氏 D Shore D	D2240	52	53	53	44	-	-	-	-	59
添 加 剂 Additives	A/B (Antiblocking Agent) SLIP (Slip Agent)	A/B	-	○	-	-	○	-	○	-	-
		SLIP	○	○	-	-	○	-	○	-	-

MD*: Machine Direction MD*: 吹膜加工方向
TD**: Transverse Direction TD**: 吹膜横切方向
F50*: 50% failure F50*: 50%破裂或脆裂

据本公司所知，上述数据应属正确无误，惟因使用时之情况非受本公司管制，所以本公司对上述所作之一切建议，恕不负保证之责。使用上述或其它来源之数据，所发生之一切责任，概与本公司无涉，所有风险，应由使用者自行承担。再者，本数据所述事项，绝不能解释为诱导或建议使用与现在或未来的专利权有抵触之任何加工方法或产品。To our best knowledge, the information contained herein is true and accurate. However, since conditions of use are beyond our control, all recommendations or suggests are presented without guarantee or responsibility on our part. We disclaim all liability in connection with the use of information contained herein or otherwise. All risks of such use are assumed by the user. Furthermore, nothing contained herein shall be construed as an inducement or recommendation to be used in any process or any product in conflict with existing or future patents.